

HOW TO USE

THE SILQ THEORY SYSTEM

FROM PREPARATION TO FINISH



THE COMPLETE SYSTEM

01

PREP

240 grit

02

PRIME

Acid-Free Primer

03

BASE

Flex Base

04

BUILD

Builder Gel

05

REFINE

180 / 240 grit

06

FINISH

Crystal Top

MADE TO SIMPLIFY YOUR WORK.

NAIL PREPARATION

SILQ THEORY 180 / 240 FILE


02



THE APPLICATION

- 1 PREPARE**
Gently remove the shine using the softer 240-grit side of the file.
- 2 CLEAN**
Remove all dust from the nail plate.
- 3 CHECK**
Make sure the nail plate is ready for primer.

KEY MOMENTS



KEEP IN MIND

- Work with light pressure.
- Do not over-file the natural nail.
- For a fill, prep only the new growth.
- For a new set on bare nails, prep the entire nail plate.

ACID-FREE PRIMER

AIR-DRY ADHESION STEP



03



THE APPLICATION

- 1 APPLY**
Apply a small amount to the natural nail.
- 2 AIR DRY**
Allow the primer to air dry.
- 3 CONTINUE**
Leave the sticky layer in place. Do not remove it.

KEY MOMENTS



KEEP IN MIND

- A small amount is enough.
- Avoid contact with the surrounding skin.

FLEX BASE

THIN, EVEN APPLICATION


04



THE APPLICATION

- 1 APPLY**
Apply a thin, even layer of Flex Base without rubbing it into the nail plate.
- 2 COVER**
Distribute the product evenly across the natural nail.
- 3 CURE**
Cure completely before applying Builder Gel: 60 seconds in an LED lamp or 120 seconds in a UV lamp.

KEY MOMENTS



KEEP IN MIND

- Keep the layer thin and even.
- Do not use Flex Base for leveling or building structure.

BUILDER GEL OVERLAY

SILQ THEORY BUILDER GEL



05



THE APPLICATION

- 1 APPLY**
Apply Builder Gel over the prepared nail.
- 2 LEVEL**
Allow the gel to self-level.
- 3 CURE**
Cure completely in the lamp.

KEY MOMENTS



CURING

- LED lamp: 60 seconds
- UV lamp: 120 seconds

KEEP IN MIND

- Use only the amount needed.
- Keep the gel away from the surrounding skin.

BUILDER GEL + DUAL FORMS

SQUARE OR ALMOND


06



THE APPLICATION

- 1 ADD PRODUCT**
Place Builder Gel inside the selected dual form.
- 2 POSITION**
Place the form onto the prepared nail.
- 3 HOLD**
Keep the form in place without excessive pressure.

KEY MOMENTS



CURING

- Flash cure: about 8 seconds
- Full cure: 60 seconds in an LED lamp or 120 seconds in a UV lamp.

KEEP IN MIND

- Do not use too much product.
- Do not overpress the form.

SHAPING + REFINING

SILQ THEORY 180 / 240 FILE


07



THE APPLICATION

- 1 SHAPE**
Use the 180-grit side to refine the length and shape.
- 2 SMOOTH**
Use the 180-grit side to refine the length and shape.
- 3 CLEAN**
Remove all filing dust before applying Crystal Top.

KEY MOMENTS



KEEP IN MIND

- File only where refinement is needed.
- Use controlled pressure.

CRYSTAL TOP

NON-WIPE GLOSS WITH UV FILTERS



08



THE APPLICATION

- 1 APPLY**
Apply a thin, even layer of Crystal Top.
- 2 COVER**
Cover the entire nail evenly.
- 3 CURE**
Cure completely in the lamp: 60 seconds in an LED lamp or 120 seconds in a UV lamp.

KEY MOMENTS



KEEP IN MIND

- Avoid contact with the surrounding skin.
- Before curing, briefly turn the hand palm up to help Crystal Top self-level.

THE FINAL RESULT

REFINE · PREPARE · PHOTOGRAPH

09



YOUR WORK DESERVES TO BE SEEN

Beautiful photos help future clients imagine the result on their own hands — and turn finished sets into future bookings.

FINAL TOUCHES

01

FINAL CHECK

After curing, check the shape and lightly refine the free edge if needed.

02

PREPARE

Remove any dust, cleanse the hands, and apply cuticle oil for a polished finish.

03

CAPTURE

Use even lighting and a simple background to keep the focus on the finished result.

[SHOP THE SYSTEM](#)

